

Plastic Extruders Ltd


Russell Gardens, Wickford, Essex, SS11 8DN, England
 Sales Tel: +44(0)1268 571116 Fax: +44(0)1268 560027
 www.plastex.co.uk e-mail: sales@plastex.co.uk




Nov-12

PRODUCT DATA SHEET: Herongripa

Sizes & weights <i>All dimensions are nominal</i>	Tolerances	Length	Height	Widths			Weight kg/m ²
		0+0.3	+/-0.5	+/- 1			
		m	mm	cm			
Herongripa		5 & 10	15	60	91	122	4.0



Herongripa



General

APPEARANCES	Open grid "duckboard" design with textured surface.
COLOURS	Available in homogenous standard colour; Terracotta.
DURABILITY	One piece welded construction for maintenance free life.
WORKABILITY	Available in rolls for ease of installation. Easy to cut to size and shape.
USES	For food processing areas.

Technical data

ACOUSTIC	Excellent sound absorption properties.
CHEMICAL	Resistant to most acids, alkalines and oils. For specific chemical resistances, see www.plastexmatting.com/matfax/doc.php?doc_id=154&action=inline
COMPOSITION	Flexible animal fat resistant DINP plasticised Polyvinyl Chloride (PVC) with Steritouch additives.
ENVIRONMENT	Plastex does not use any substances currently included in the SVHC (Substances of Very High Concern) list under R.E.A.C.H.* in any matting products. All products are 100% recyclable. * Registration, Evaluation, Authorisation and Restriction of Chemical substances
HYGIENE	Non-porous 100% Virgin PVC - Inhibits the growth of bacteria.
Anti-bacterial	SteriTouch additive; Test JIS Z 2801:2000 - Determination of the antibacterial effect against: Staphylococcus aureus Result - Antimicrobial pass of >99% E. Coli Result - Antimicrobial pass of >99.99%
Anti-fungal	SteriTouch additive; Test method ASTM G21-96 - Determining resistance to fungi. Result - Nil Growth after 4 weeks
REVERSION	Thermoplastic shrinkage can result in size reductions up to 2%. Accelerated in hot environments (refer to www.plastexmatting.com/matfax/doc.php?doc_id=254&action=inline).
SLIP RESISTANCE	DIN 51130: R11, V10
THERMAL	Functional -23°C +60°C (slight size variation may occur at temperature extremes).
UV LIGHT	Resistant to PVC degradation; uncoloured PVC material - BS EN 607 = Delta E 1.02.
WARRANTY	3 years. See www.plastexmatting.com/matfax/doc.php?doc_id=167&action=inline